ECHNICAL SPECIFICATIONS	NORMAL VALUE
olour	green
dielectric strength	>20 kV/mm
working time at 25 °C	15 min
cross-linking time at 25 °C	25 min
density	1,37 g/cm ^s
SHORE D hardness	55
she l f life	3 years



RS

Two-component solid-final state polyurethane resin in bags





Applications

 All types of filling and insulation of electrical connection and junction boxes with operating voltages of up to 1 kV

Package contents

- Bag with removable baffle
- Perforated Casting System (PCS)
- Instructions

Advantages

- Watertight seal of the box and/or connection
- Excellent mechanical protection thanks to the solid final state
- Casting of the resin is fluid and homogeneous, without accidental spills, thanks to the Perforated Casting System (PCS)

SELECTION TABLE		
item	weight (g)	volume (litres)
RS-150	150	0,110
RS-300	300	0.220
RS-400	400	0.290
RS-550	550	0.400
RS-650	650	0.470
RS-1650	1650	1,200

